



Quality Paints since 1845
MATHYS®



PARACEM® DECO PLAFOND

One-coat ceiling paint

- Exceptional high covering power (covers mostly in 1 layer)
- Uniform matt finish without laps
- Delayed drying (enables to paint large surfaces)
- Odourless
- Extra matt

PARACEM® DECO PLAFOND

POPIS PRODUKTU (DLOUHÝ)

Paracem Deco Plafond is a super covering and extra matt acrylic paint for ceilings and inner walls. Applicable on most mineral substrates.

DOPORUČENÉ POUŽITÍ

For indoor walls and ceilings: on plaster, plasterboard, rendering, bricks, concrete, etc. as well as on old paints, wallpaper, ingrain wallpaper, etc.

TECHNICAL DATA

Hustota (g/cm ³):	1,41 - 1,45
Úroveň lesku:	Matt
Úroveň lesku při 60°:	Matt: 2%
Obsah pevných látek v hmotnosti:	52 - 54%
Obsah pevných látek v objemu:	32 - 34%

DRY TIMES BY 20

Dotykem suché:	2 hours
Suchý nátěr:	4 hours
Plně vytvrzené:	1 day

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

140 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

45 µm

TEORETICKÁ SPOTŘEBA

6 - 8 m²/l per coat

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity, roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

The surface must be dry and free of dust and grease.

You can paint Paracem® Deco Soft Plafond directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous. You must treat porous surfaces with Paracem® Deco Primer first.

Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first.

Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus).

Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Minimum 5°C / Maximum 80% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

If necessary, dilute with some water.

Nozzle: 011 - 013 / Pressure: 200 bars, dilute with maximum 3% volume water.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

DATA SAFETY DATA

Úroveň těkavých organických

látek: 28 g/l

VOC readymix: 29 g/l

Kategorie VOC: A/a

Limitní hodnota VOC: 30 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production when kept in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu