



Quality Paints since 1845  
**MATHYS**®



## PARACEM® DECO PLAFOND

### One-coat ceiling paint

- Exceptional high covering power (covers mostly in 1 layer)
- Uniform matt finish without laps
- Delayed drying (enables to paint large surfaces)
- Odourless
- Extra matt

# PARACEM® DECO PLAFOND

## POPIS PRODUKTU (DLHÝ)

Paracem Deco Plafond is a super covering and extra matt acrylic paint for ceilings and inner walls. Applicable on most mineral substrates.

## ODPORÚČANÉ POUŽITIE

For indoor walls and ceilings: on plaster, plasterboard, rendering, bricks, concrete, etc. as well as on old paints, wallpaper, ingrain wallpaper, etc.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,41 - 1,45
Úroveň lesku:	Matt
Úroveň lesku pri 60°:	Matt: 2%
Obsah pevných látok v hmotnosti:	52 - 54%
Obsah pevných látok v objeme:	32 - 34%

## DRY TIMES BY 20

Na dotyk suché:	2 hours
Suchý na opätovné natieranie:	4 hours
Úplne vytvrdené:	1 day

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

140 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

45 µm

## TEORETICKÁ SPOTREBA

6 - 8 m<sup>2</sup>/l per coat

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity, roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

The surface must be dry and free of dust and grease.

You can paint Paracem® Deco Soft Plafond directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous. You must treat porous surfaces with Paracem® Deco Primer first.

Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first.

Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus).

Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

Minimum 5°C / Maximum 80% R.H.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted.

## APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

If necessary, dilute with some water.

Nozzle: 011 - 013 / Pressure: 200 bars, dilute with maximum 3% volume water.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

## DATA SAFETY DATA

Úroveň VOC:	28 g/l
VOC readymix:	29 g/l
Kategória VOC:	A/a
Limit VOC:	30 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production when kept in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu