



Quality Paints since 1845
MATHYS[®]

PARACEM[®] DECO PRIMER

Water-based primer based on acrylic dispersions

- Reduces absorption
- Neutralises differences in absorption characteristics
- Prevents differences in the glossiness of the topcoat
- Very good hiding characteristics
- Improves topcoat adhesion



PARACEM® DECO PRIMER

POPIS PRODUKTU (DLHÝ)

Water-based primer based on acrylic dispersions. Neutralises differences in the absorption characteristics of the substrate.

ODPORÚČANÉ POUŽITIE

Indoors, on various porous, unpainted surfaces (for example brick, slab work, concrete) before finishing them off with water-based paints

TECHNICAL DATA

Hustota (g/cm ³):	± 1,35 (white - wit - blanc)
Úroveň lesku:	Matt
Úroveň lesku pri 60°:	Matt: 5%
Obsah pevných látok v hmotnosti:	58% (white - wit - blanc)
Obsah pevných látok v objeme:	45% (white - wit - blanc)

DRY TIMES BY 20

Na dotyk suché:	1,5 hours
Suchý na opätovné natieranie:	2-3 hours
Úplne vytvrdnuté:	1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

45 µm

TEORETICKÁ SPOTREBA

8 - 10 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

PRÍPRAVA POVRCHU

Clean the substrate and remove all grease. Paracem Deco Primer may be directly applied over lightly porous substrates and old, cleaned paint layers if they are in good condition. Highly porous substrates, smooth plaster and water-resistant gypsum board: use Pegafix in 1 or 2 layers of Paracem Deco Primer. Block water or nicotine stains with Pegamat RL, or Zinsser primers 123 Plus or B.I.N.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Apply at a temperature of minimum 5°C and a R.H. of maximum 80%

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted.

APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Apply undiluted.

Nozzle: 011 - 015 / Pressure: 180 - 200 bar.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Apply undiluted.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water

DATA SAFETY DATA

Úroveň VOC:	30 g/l
VOC readymix:	30 g/l
Kategória VOC:	A/g
Limit VOC:	30 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production when kept in unopened cans, original packaging, stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu