



Quality Paints since 1845
MATHYS[®]

PARACEM[®] DECO PRIMER

Water-based primer based on acrylic dispersions

- Reduces absorption
- Neutralises differences in absorption characteristics
- Prevents differences in the glossiness of the topcoat
- Very good hiding characteristics
- Improves topcoat adhesion



PARACEM® DECO PRIMER

BESKRIVNING

Water-based primer based on acrylic dispersions. Neutralises differences in the absorption characteristics of the substrate.

REKOMMENDERAD ANVÄNDNING

Indoors, on various porous, unpainted surfaces (for example brick, slab work, concrete) before finishing them off with water-based paints

TEKNISK DATA

Densitet:	± 1,35 (white - wit - blanc)
Glansnivå:	Matt
Glansnivå vid 60°:	Matt: 5%
Torrsubstansvikt:	58% (white - wit - blanc)
Torrsubstansvolym:	45% (white - wit - blanc)

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1,5 hours
Övermålningsbar:	2-3 hours
Fullt härdad:	1 week

REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

45 µm

TEORETISK FÖRBRUKNING

8 - 10 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

YTFÖRBEREDELSE

Clean the substrate and remove all grease. Paracem Deco Primer may be directly applied over lightly porous substrates and old, cleaned paint layers if they are in good condition. Highly porous substrates, smooth plaster and water-resistant gypsum board: use Pegafix in 1 or 2 layers of Paracem Deco Primer. Block water or nicotine stains with Pegamat RL, or Zinsser primers 123 Plus or B.I.N.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Apply at a temperature of minimum 5°C and a R.H. of maximum 80%

APPLICERING OCH SPÄDNING: PENSEL

Apply undiluted.

APPLICERING OCH SPÄDNING: ROLLER

Apply undiluted.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Apply undiluted.

Nozzle: 011 - 015 / Pressure: 180 - 200 bar.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Apply undiluted.

RENGÖRING AV UTRUSTNING/SPILL

Water

SÄKERHETSDATA

VOC-nivå:	30 g/l
VOC färdigmix:	30 g/l
VOC-kategori:	A/g
VOC-gräns:	30 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production when kept in unopened cans, original packaging, stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskadorna. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu