



## PARACEM<sup>®</sup> DECO SATIN

# High-quality satin gloss interior wall paint

- Excellent flow
- Good mechanical resistance against rubbing
- Smooth satin aspect
- Closed coating structure
- Washable

# PARACEM® DECO SATIN

## POPIS PRODUKTU (DLOUHÝ)

High-quality satin gloss interior wall paint

## DOPORUČENÉ POUŽITÍ

Decorative and satin finishing for indoor walls and ceilings.

Applicable on most substrates (plaster, bricks, concrete, glass fibre etc.) in residential and public buildings.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,32 - 1,36 (white - wit - blanc)
Úroveň lesku:	Satin
Úroveň lesku při 60°:	Satin Gloss: 25-30%
Úroveň lesku při 85°:	Satin Gloss: 45-50%
Obsah pevných látek v hmotnosti:	57 - 59% (white - wit - blanc)
Obsah pevných látek v objemu:	42 - 44% (white - wit - blanc)
Odolnost proti drhnutí za mokra (EN 13300):	wsr_c1

## DRY TIMES BY 20

Dotykem suché:	1 hour
Suchý nátěr:	2 hours
Plně vytvrzené:	2 days

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

140 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

60 µm

## TEORETICKÁ SPOTŘEBA

6 - 10 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

The surface must be dry and free of dust and grease.

You can paint Paracem® Deco Satin directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous.

You must treat porous surfaces with Paracem® Deco Primer first.

Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first.

Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus).

Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123.

On glass fibre, apply preferably first a coat of Paracem® Deco Primer or Zinsser primers Bulls Eye 123 or 123 Plus before finishing with 2 coats of Paracem® Deco Satin.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

> 5°C, < 80% R.H.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 013 - 019 / Pressure: 160 - 200 bars.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

If required dilute with water.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

## POZNÁMKY

In case of application on patterned vinyl wallpaper, Pegaprim Isofix should be used to block plasticizers migration and limit tacking effect.

## DATA SAFETY DATA

Úroveň těkavých organických

látek: 30 g/l

VOC readymix: 30 g/l

Kategorie VOC: A/b

Limitní hodnota VOC: 100 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu

# PARACEM® DECO SATIN

## DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu