

Quality Paints since 1845
MATHYS[®]



PARACEM[®] DECO ULTRA CLEAN

Washable interior wall paint with a matt finish

- Excellent cleanability
- Excellent mechanical resistance against rubbing
- Low dirt pick up
- Easy to apply
- Excellent flow

PARACEM® DECO ULTRA CLEAN

BESKRIVNING

Paracem® Deco Ultra Clean is a washable waterborne acrylic interior wall paint with a matt finish. This decorative paint is available in white and in almost every colour, from light to dark tints.

REKOMMENDERAD ANVÄNDNING

Ideal finish for the walls of interior rooms that require regular cleaning (e.g. children's rooms, kitchens,...). Suitable for use on most substrates (plaster, bricks, concrete, etc.) in private and in public buildings.

TEKNISK DATA

Densitet:	1,36 - 1,40 (white - wit - blanc)
Glansnivå:	Matt
Glansnivå vid 60°:	Matt: 1-2%
Glansnivå vid 85°:	Matt: 2,5-3,5%
Torrsubstansvikt:	60,5 - 62,5% (white)
Torrsubstansvolym:	49 - 51% (white)

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	30 minutes
Övermålningsbar:	1 hour
Fullt härdad:	7 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

50 µm

TEORETISK FÖRBRUKNING

7 - 10 m²/l per coat

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

The surface must be dry and free of dust and grease.

You can paint Paracem® Deco Ultra Clean directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous.

You must treat porous surfaces with Paracem® Deco Primer first.

Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first.

Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus).

Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123.

On glass fibre, apply preferably first a coat of Paracem® Deco Primer or Zinsser primers Bulls Eye 123 or 123 Plus before finishing with 2 coats of Paracem® Deco Ultra Clean.

When working in combination with a joint sealant, we recommend using our acrylic sealant Elastopro, which can be painted over after drying for at least 1 hour (20°C, 60% r.h.).

BRUKSANVISNING

To ensure homogeneity, thoroughly stir prior to use. Apply two layers of Paracem Deco Ultra Clean. For best result use a brush with synthetic bristles or a 10 mm micro fiber roller.

APPLICERINGSFÖRHÅLLANDEN

> 5°C, < 80% R.H.

APPLICERING OCH SPÅDNING: PENSEL

Apply undiluted with brush with synthetic bristles.

APPLICERING OCH SPÅDNING: AIRLESSPRUTA

Nozzle: 013 - 019 / Pressure: 160 - 200 bars.

APPLICERING OCH SPÅDNING: TRYCKLUFTSSPRUTA

not recommended.

RENGÖRING AV UTRUSTNING/SPILL

Clean tools with water, dispose of residue in the appropriate manner.

ANMÄRKNINGAR

Cleaning instructions: Remove the contamination as soon as possible. Most contamination can easily be removed with a soft, damp cloth. Use lukewarm water and a mild colourless detergent. Do not use abrasive cleaning products. Do not use excessive pressure when cleaning as this may result in removing paint which will leave marks.

For more serious contaminations first wipe the substrate with a soft damp cloth, then use Mathys Multi-cleaner (diluted 1:100). Allow to dry.

The best cleaning results are achieved after the Paracem® Deco Ultra Clean has dried for minimum 7 days.

Although extensive evaluations have been undertaken to ensure the cleanability of the Paracem® Deco Ultra Clean it might be possible that some contamination is difficult to remove and leaves traces.

Touching the paint may leave marks this is due to the matt nature of the product (the marks will be more visible on dark colours).

SÄKERHETSDATA

VOC-nivå:	15 g/l
VOC färdigmix:	15 g/l
VOC-kategori:	A/a
VOC-gräns:	30 g/l
Anmärkingar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.

Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.

38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.

Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu