



Quality Paints since 1845
MATHYS[®]



PARACEM[®] SEMI-MATT

Acrylic exterior wall paint with high covering power



- High durability
- Perfect saponification resistance
- Particularly high covering capacity
- Sufficiently breathing (water vapour permeable)
- Hardly permeable to rain Excellent weather resistance

PARACEM® SEMI-MATT

BESKRIVELSE

- Acrylic exterior wall paint with high covering power
- Acrylic paint for outside and inside use

ANBEFALT BRUK

For old or new substrates like masonry, cement rendering or plaster, concrete, tiles, plaster boards and wooden panels.

TEKNISKE DATA

Tetthet:	1,5
Glansgrad:	semi_mat
Glansgrad ved 60°:	5%
Tørrstoffinnhold i vekt:	64%
Tørrstoffinnhold i volum:	46%
Vanddampermeabilitet:	23g/m ² /24h and Sd (m) = 1,0

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	40 minutes (10 m ² /l)
Håndterbar:	2 hours (10 m ² /l)
Overmalbar:	4 hours (10 m ² /l)
Herdetid:	1 day

ANBEFALT VÅTFILMTYKKELSE

100 micron (cons.: 10 m²/l)

ANBEFALT TØRRFILMTYKKELSE

45 micron (cons.: 10 m²/l)

TEORETISK FORBRUK

7 - 10 m²/l per coat

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

The substrate must be sufficiently dry and stable; clean thoroughly. In case of fungal growth: treat first with an adequate moss-preventing product. On porous substrates apply first a coat of Parafix or Pegafix / Paracem (25 / 75). On very smooth bricks, apply a first coat of Noxyde diluted with 25% water, or a coat of Pegalink. Impregnate old chalking paints, after cleaning, with a coat of Fixonal or Pegafix. For stain, graffiti blocking and/or very fast recoating on all substrates, for interior or exterior, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain. Fill up holes and seal joints or fissures with Elastofill. If necessary, fill with Pegaflex. Flat down and remove dust. Hereafter, apply 1 - 2 coats of Paracem.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Minimum 5C / Maximum 80 % R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply with flat brush

PÅFØRING & FORTYNNING: RULLE

Apply with dispersion roller.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 013 - 018 / Pressure: 180 bars.

PÅFØRING & FORTYNNING: FORSTØVNINGS-SPRØYTE

Dilute with water (3 - 5% volume).

RENGJØRING AV UTSTYR/SPILL

Water.

SIKKERHETSDATA

VOC nivå:	25 g/l max.
VOC kategori:	A/c
VOC grense:	75 g/l (2007) / 40 g/l (2010)
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu