

Quality Paints since 1845
MATHYS[®]



PARACEM[®] QUARTZ

Dispersion paint with quartz effect

- Perfect saponification resistance
- durable
- fine quartz finish
- excellent weather resistance

PARACEM® QUARTZ

BESKRIVELSE

Dispersion paint with quartz effect for outside and inside use.

ANBEFALT BRUK

For protection of old deteriorated or cracked walls. Protection of concrete cell blocks against weather influences.

TEKNISKE DATA

Tetthet:	± 1,65
Tørrstoffinnhold i vekt:	73 - 75 %
Tørrstoffinnhold i volum:	55 - 59 %

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 hour
Overmalbar:	8 hours
Herdetid:	1 day

ANBEFALT VÅTFILMTYKKELSE

300 µm

ANBEFALT TØRRFILMTYKKELSE

175 µm

TEORETISK FORBRUK

500 g/m² on even flat substrates. Minimum 1 kg/m² on structured substrates such as concrete cell blocks

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Cell concrete blocks: prime with Martin Mathys Pegafix or Primer 44HS

Walls in poor condition: remove all old coatings or bad plasterwork. Sand/treat the wall with a wire brush to remove all loose particles. Repair all damaged parts with a cement mortar or Martin Mathys Pegacrete. Small repairs can be treated with a mix of Paracem Quartz filled with dry sharp sand. All repairs should be primed with Martin Mathys Pegafix. Fill up holesand seal joints or fissures with Martin Mathys Elastofill.

New walls/masonry: if possible wait 1 year before treatment. The substrate must be sufficiently dry and stable and no bleeding of nitric acid should be visible.

Brush dry and dust, then apply a coat of Martin Mathys Pegafix or Primer 44 HS.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

> 5°C, < 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply with flat brush.

PÅFØRING & FORTYNNING: RULLE

Apply with a mohair paint roller. When the applied paint film is still wet, roll a again with a slightly wet plastic foam roller for a good and equal finish.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Not advisable.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Possible with an opening diameter: 2 - 4 mm.

RENGJØRING AV UTSTYR/SPILL

Water.

SIKKERHETSDATA

VOC nivå:	30 g/l
VOC ferdigblandet:	30 g/l
VOC kategori:	A/c
VOC grense:	40 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu