

Quality Paints since 1845
MATHYS[®]



PARACEM[®] QUARTZ

Dispersion paint with quartz effect

- Perfect saponification resistance
- durable
- fine quartz finish
- excellent weather resistance

PARACEM® QUARTZ

POPIS PRODUKTU (DLHÝ)

Dispersion paint with quartz effect for outside and inside use.

ODPORÚČANÉ POUŽITIE

For protection of old deteriorated or cracked walls. Protection of concrete cell blocks against weather influences.

TECHNICAL_DATA

Hustota (g/cm³): ± 1,65
Obsah pevných látok v hmotnosti: 73 - 75 %
Obsah pevných látok v objeme: 55 - 59 %

DRY_TIMES_BY_20

Na dotyk suché: 1 hour
Suchý na opätovné natieranie: 8 hours
Úplne vytvrdnuté: 1 day

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

300 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

175 µm

TEORETICKÁ SPOTREBA

500 g/m² on even flat substrates. Minimum 1 kg/m² on structured substrates such as concrete cell blocks

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Cell concrete blocks: prime with Martin Mathys Pegafix or Primer 44HS
Walls in poor condition: remove all old coatings or bad plasterwork. Sand/treat the wall with a wire brush to remove all loose particles. Repair all damaged parts with a cement mortar or Martin Mathys Pegacrete. Small repairs can be treated with a mix of Paracem Quartz filled with dry sharp sand. All repairs should be primed with Martin Mathys Pegafix. Fill up holes and seal joints or fissures with Martin Mathys Elastofill.
New walls/masonry: if possible wait 1 year before treatment. The substrate must be sufficiently dry and stable and no bleeding of nitric acid should be visible.
Brush dry and dust, then apply a coat of Martin Mathys Pegafix or Primer 44 HS.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

> 5°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply with flat brush.

APLIKÁCIA A RIEDENIE: VALEC

Apply with a mohair paint roller. When the applied paint film is still wet, roll a again with a slightly wet plastic foam roller for a good and equal finish.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Not advisable.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Possible with an opening diameter: 2 - 4 mm.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

DATA SAFETY DATA

Úroveň VOC: 30 g/l
VOC readymix: 30 g/l
Kategória VOC: A/c
Limit VOC: 40 g/l
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu