

Quality Paints since 1845
MATHYS[®]



PARACEM[®] SEMI-GLOSS

Waterborne semi-gloss acrylic paint



- For indoor and outdoor works
- Very decorative semi-gloss aspect
- Easy to clean and to maintain
- High filling and hiding power
- Excellent flow out

PARACEM® SEMI-GLOSS

POPIS PRODUKTU (DLOUHÝ)

Waterborne semi-gloss acrylic paint for inner and outer walls.

DOPORUČENÉ POUŽITÍ

Durable painting of old and new masonry, cement, concrete or plaster.

DOPORUČENÝ SYSTÉM

Substrate/Condition	Primer/Preparation	Finish
Porous substrates	Pegafix or Parafix/Paracem (50/50)	2 coats Paracem SG
Very smooth/non porous	Noxyde diluted with 25% water or Pegalink	2 coats Paracem SG
Sound old paints (no chalking)	-	2 coats Paracem SG
Sound old paints (chalking)	Fixonal or Pegafix	2 coats Paracem SG
Cracks and holes	Fill with Elastofill or Mur-Filler	-
Uneven substrate	Fill with Pegaflex. Sand, remove dust and prime with	2 coats Paracem SG

TECHNICAL DATA

Hustota (g/cm ³):	1,28 - 1,32
Úroveň lesku:	Satin
Úroveň lesku při 60°:	Semi-Gloss: 65%
Obsah pevných látek v hmotnosti:	50 -53 %
Obsah pevných látek v objemu:	35 - 38 %

DRY TIMES BY 20

Dotykem suché:	40 minutes
Suché na manipulaci:	2 hours
Suchý nátěr:	4 hours
Plně vytvrzené:	1 day

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

125 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

45 µm

TEORETICKÁ SPOTŘEBA

8 - 10 m²/l

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

The substrate must be sufficiently dry (max. 4% moisture content) and stable. Clean walls thoroughly with steel brush or high pressure water cleaning. In case of fungal growth: treat the walls first with an adequate moss-preventing product.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

> 5°C, < 80% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply in 2 coats by preference. Use a synthetic brush for application of waterbased products.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply in 2 coats by preference. Use short nap roller (texture polyamide roller 14 mm).

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 018 / Pressure: 180 bars. 1 coat is sufficient in most cases.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

DATA SAFETY DATA

Úroveň těkavých organických látek:	15 g/l
VOC readymix:	15 g/l
Kategorie VOC:	A/c
Limitní hodnota VOC:	40 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu