

Quality Paints since 1845
MATHYS[®]



PARACEM[®] SEMI-GLOSS

Waterborne semi-gloss acrylic paint



- For indoor and outdoor works
- Very decorative semi-gloss aspect
- Easy to clean and to maintain
- High filling and hiding power
- Excellent flow out

PARACEM® SEMI-GLOSS

BESKRIVELSE

Waterborne semi-gloss acrylic paint for inner and outer walls.

ANBEFALT BRUK

Durable painting of old and new masonry, cement, concrete or plaster.

ANBEFALT SYSTEM

| Substrate/Condition | Primer/Preparation | Finish |
|--------------------------------|--|--------------------|
| Porous substrates | Pegafix or Parafix/Paracem (50/50) | 2 coats Paracem SG |
| Very smooth/non porous | Noxyde diluted with 25% water or Pegalink | 2 coats Paracem SG |
| Sound old paints (no chalking) | - | 2 coats Paracem SG |
| Sound old paints (chalking) | Fixonal or Pegafix | 2 coats Paracem SG |
| Cracks and holes | Fill with Elastofill or Mur-Filler | - |
| Uneven substrate | Fill with Pegaflex. Sand, remove dust and prime with | 2 coats Paracem SG |

TEKNISKE DATA

| | |
|----------------------------|-----------------|
| Tetthet: | 1,28 - 1,32 |
| Glansgrad: | Satinert |
| Glansgrad ved 60°: | Semi-Gloss: 65% |
| Tørrestoffinnhold i vekt: | 50 -53 % |
| Tørrestoffinnhold i volum: | 35 - 38 % |

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

| | |
|-------------|------------|
| Støvtørr: | 40 minutes |
| Håndterbar: | 2 hours |
| Overmalbar: | 4 hours |
| Herdetid: | 1 day |

ANBEFALT VÅTFILMTYKKELSE

125 µm

ANBEFALT TØRRFILMTYKKELSE

45 µm

TEORETISK FORBRUK

8 - 10 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

The substrate must be sufficiently dry (max. 4% moisture content) and stable. Clean walls thoroughly with steel brush or high pressure water cleaning. In case of fungal growth: treat the walls first with an adequate moss-preventing product.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

> 5°C, < 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply in 2 coats by preference. Use a synthetic brush for application of waterbased products.

PÅFØRING & FORTYNNING: RULLE

Apply in 2 coats by preference. Use short nap roller (texture polyamide roller 14 mm).

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 018 / Pressure: 180 bars. 1 coat is sufficient in most cases.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Not recommended.

RENGJØRING AV UTSTYR/SPILL

Water.

SIKKERHETSDATA

| | |
|-------------------------------|--|
| VOC nivå: | 15 g/l |
| VOC ferdigblandet: | 15 g/l |
| VOC kategori: | A/c |
| VOC grense: | 40 g/l |
| Merknader angående sikkerhet: | Consult Safety Data Sheet and Safety Information printed on the can. |

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu