

Quality Paints since 1845
MATHYS[®]



PARACEM[®] SEMI-GLOSS

Waterborne semi-gloss acrylic paint



- For indoor and outdoor works
- Very decorative semi-gloss aspect
- Easy to clean and to maintain
- High filling and hiding power
- Excellent flow out

PARACEM® SEMI-GLOSS

POPIS PRODUKTU (DLHÝ)

Waterborne semi-gloss acrylic paint for inner and outer walls.

ODPORÚČANÉ POUŽITIE

Durable painting of old and new masonry, cement, concrete or plaster.

ODPORÚČANÝ SYSTÉM

Substrate/Condition	Primer/Preparation	Finish
Porous substrates	Pegafix or Parafix/Paracem (50/50)	2 coats Paracem SG
Very smooth/non porous	Noxyde diluted with 25% water or Pegalink	2 coats Paracem SG
Sound old paints (no chalking)	-	2 coats Paracem SG
Sound old paints (chalking)	Fixonal or Pegafix	2 coats Paracem SG
Cracks and holes	Fill with Elastofill or Mur-Filler	-
Uneven substrate	Fill with Pegaflex. Sand, remove dust and prime with	2 coats Paracem SG

TECHNICAL DATA

Hustota (g/cm ³):	1,28 - 1,32
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	Semi-Gloss: 65%
Obsah pevných látok v hmotnosti:	50 -53 %
Obsah pevných látok v objeme:	35 - 38 %

DRY TIMES BY 20

Na dotyk suché:	40 minutes
Suché na manipuláciu:	2 hours
Suchý na opätovné natieranie:	4 hours
Úplne vytvrdené:	1 day

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

125 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

45 µm

TEORETICKÁ SPOTREBA

8 - 10 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

The substrate must be sufficiently dry (max. 4% moisture content) and stable. Clean walls thoroughly with steel brush or high pressure water cleaning. In case of fungal growth: treat the walls first with an adequate moss-preventing product.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

> 5°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply in 2 coats by preference. Use a synthetic brush for application of waterbased products.

APLIKÁCIA A RIEDENIE: VALEC

Apply in 2 coats by preference. Use short nap roller (texture polyamide roller 14 mm).

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 018 / Pressure: 180 bars. 1 coat is sufficient in most cases.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

DATA SAFETY DATA

Úroveň VOC:	15 g/l
VOC ready mix:	15 g/l
Kategória VOC:	A/c
Limit VOC:	40 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu