

Quality Paints since 1845
MATHYS[®]



PARACEM[®] SEMI-GLOSS

Waterborne semi-gloss acrylic paint



- For indoor and outdoor works
- Very decorative semi-gloss aspect
- Easy to clean and to maintain
- High filling and hiding power
- Excellent flow out

PARACEM® SEMI-GLOSS

BESKRIVNING

Waterborne semi-gloss acrylic paint for inner and outer walls.

REKOMMENDERAD ANVÄNDNING

Durable painting of old and new masonry, cement, concrete or plaster.

REKOMMENDERAT SYSTEM

Substrate/Condition	Primer/Preparation	Finish
Porous substrates	Pegafix or Parafix/Paracem (50/50)	2 coats Paracem SG
Very smooth/non porous	Noxyde diluted with 25% water or Pegalink	2 coats Paracem SG
Sound old paints (no chalking)	-	2 coats Paracem SG
Sound old paints (chalking)	Fixonal or Pegafix	2 coats Paracem SG
Cracks and holes	Fill with Elastofill or Mur-Filler	-
Uneven substrate	Fill with Pegaflex. Sand, remove dust and prime with	2 coats Paracem SG

TEKNISK DATA

Densitet:	1,28 - 1,32
Glansnivå:	Satin
Glansnivå vid 60°:	Semi-Gloss: 65%
Torrsubstansvikt:	50 -53 %
Torrsubstansvolym:	35 - 38 %

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	40 minutes
Hanteringstorr:	2 hours
Övermålningsbar:	4 hours
Fullt härdad:	1 day

REKOMMENDERAD VÅTFILMSTJOCKLEK

125 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

45 µm

TEORETISK FÖRBRUKNING

8 - 10 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

The substrate must be sufficiently dry (max. 4% moisture content) and stable. Clean walls thoroughly with steel brush or high pressure water cleaning. In case of fungal growth: treat the walls first with an adequate moss-preventing product.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

> 5°C, < 80% R.H.

APPLICERING OCH SPÅDNING: PENSEL

Apply in 2 coats by preference. Use a synthetic brush for application of waterbased products.

APPLICERING OCH SPÅDNING: ROLLER

Apply in 2 coats by preference. Use short nap roller (texture polyamide roller 14 mm).

APPLICERING OCH SPÅDNING: AIRLESSPRUTA

Nozzle: 018 / Pressure: 180 bars. 1 coat is sufficient in most cases.

APPLICERING OCH SPÅDNING: TRYCKLUFTSSPRUTA

Not recommended.

RENGÖRING AV UTRUSTNING/SPILL

Water.

SÄKERHETSDATA

VOC-nivå:	15 g/l
VOC färdigmix:	15 g/l
VOC-kategori:	A/c
VOC-gräns:	40 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu