



Quality Paints since 1845
MATHYS[®]



PARACEM[®] SEMI-MATT

Acrylic exterior wall paint with high covering power



- High durability
- Perfect saponification resistance
- Particularly high covering capacity
- Sufficiently breathing (water vapour permeable)
- Hardly permeable to rain Excellent weather resistance

PARACEM® SEMI-MATT

BESKRIVNING

- Acrylic exterior wall paint with high covering power
- Acrylic paint for outside and inside use

REKOMMENDERAD ANVÄNDNING

For old or new substrates like masonry, cement rendering or plaster, concrete, tiles, plaster boards and wooden panels.

TEKNISK DATA

Densitet:	1,5
Glansnivå:	Semi-Mat
Glansnivå vid 60°:	5%
Torrsubstansvikt:	64%
Torrsubstansvolym:	46%
Kondensgenomsläpplighet:	23g/m ² /24h and Sd (m) = 1,0

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	40 minutes (10 m ² /l)
Hanteringstorr:	2 hours (10 m ² /l)
Övermålningsbar:	4 hours (10 m ² /l)
Fullt härdad:	1 day

REKOMMENDERAD VÅTFILMSTJOCKLEK

100 micron (cons.: 10 m²/l)

REKOMMENDERAD TORRFILMSTJOCKLEK

45 micron (cons.: 10 m²/l)

TEORETISK FÖRBRUKNING

7 - 10 m²/l per coat

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

The substrate must be sufficiently dry and stable; clean thoroughly.
In case of fungal growth: treat first with an adequate moss-preventing product. On porous substrates apply first a coat of Parafix or Pegafix / Paracem (25 / 75). On very smooth bricks, apply a first coat of Noxyde diluted with 25% water, or a coat of Pegalink. Impregnate old chalking paints, after cleaning, with a coat of Fixonal or Pegafix. For stain, graffiti blocking and/or very fast recoating on all substrates, for interior or exterior, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain. Fill up holes and seal joints or fissures with Elastofill. If necessary, fill with Pegaflex. Flat down and remove dust. Hereafter, apply 1 - 2 coats of Paracem.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Minimum 5C / Maximum 80 % R.H.

APPLICERING OCH SPÄDNING: PENSEL

Apply with flat brush

APPLICERING OCH SPÄDNING: ROLLER

Apply with dispersion roller.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Nozzle: 013 - 018 / Pressure: 180 bars.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Dilute with water (3 - 5% volume).

RENGÖRING AV UTRUSTNING/SPILL

Water.

SÄKERHETSDATA

VOC-nivå:	25 g/l max.
VOC-kategori:	A/c
VOC-gräns:	75 g/l (2007) / 40 g/l (2010)
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.

Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.

38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.

Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu