



## PARACEM<sup>®</sup> UNIVERSAL

# Excellent covering universal paint for all outside work

- Matt universal paint for the outdoors
- Usable on all surfaces, such as bricks, gutters, wood, aluminium, etc.
- Colour and weatherproof for long-term protection
- Protection of the dried coat against contamination by mould
- Primer and finishing coat in one



# PARACEM® UNIVERSAL

## DESCRIZIONE

Excellent covering universal paint for outside work. Extremely suitable for durable decoration of woodwork, metal, bricks, plastic, concrete and more. New or already painted. Paracem® Universal is water-vapour permeable, water repellent, and requires minimum maintenance. Self-priming in most cases. Protects dry coating against contamination by mould. Paracem® Universal has a unique property, namely, the colour does not darken when the façade is wet.

## UTILIZZO CONSIGLIATO

Developed for all outside work, Paracem® Universal is ideal for applying to bricks, façade cladding, plaster, woodwork, plastic, galvanised metal, steel, concrete, and more. Paracem® Universal is self-priming and will immediately adhere to existing glossy surfaces without the need for sanding. A separate primer is unnecessary for most applications. Paracem® Universal provides excellent resistance against cracking, blistering, flaking, rain, and severe weather conditions. Two-layer system: Apply the first layer, which primes and seals the surface. The second layer completes the sealing process and provides additional moisture resistance and protection.

## DATI TECNICI

Densità:	1,25
Livello di lucentezza:	Opaco
Livello di lucentezza a 60°:	± 2%
Livello di lucentezza a 85°:	± 3%
Residuo secco in peso:	40%
Residuo secco in volume:	40%
Permeabilità al vapore acqueo:	Sd = 0,41 m

## TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto:	1 h
Asciutto da maneggiare:	1 h
Asciutto da rivestire:	1 h
Completamente indurito:	7 days

## SPESSORE DELLA PELLICOLA UMIDA CONSIGLIATO

100 µm per coat

## SPESSORE DELLA PELLICOLA ASCIUTTA CONSIGLIATO

40 µm per coat

## CONSUMO TEORICO

8-12 m<sup>2</sup>/l/coat

## CONSUMO PRATICO

Practical coverage depends on many factors such as porosity and roughness of the substrate. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

## PREPARAZIONE DELLA SUPERFICIE

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using ND14. Use AMW concentrate to remove algae and mould.

## ISTRUZIONI PER L'USO

Mix carefully before use.

## CONDIZIONI DI APPLICAZIONE

> 10°C, < 85% R.H.

## APPLICAZIONE E DILUIZIONE: PENNELLO

Apply with brush with synthetic bristles.

## APPLICAZIONE E DILUIZIONE: RULLO

Apply with synthetic roller.

## APPLICAZIONE E DILUIZIONE: SPRAY SENZ'ARIA

Nozzle: 0.017 / Pressure: 140 - 170 bar

## PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Use lukewarm soapy water to clean off stains and materials.

## NOTE

Paracem® Universal is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. Before applying Paracem® Universal, we recommend that you thoroughly sand and degrease unweathered/new powder coatings and similar surfaces. Not suitable for application onto new plastisol or a new powder coating. These surfaces must be fully weathered. Paracem® Universal has no anti corrosive properties, so don't apply directly on ferrous metal surfaces, but always use an appropriate anticorrosive primer like Metal Cladding Primer. Specific substrates like enamelled bricks require an adhesion coat with diluted Noxyde.

## DATI RELATIVI ALLA SICUREZZA

Livello di COV:	35 g/l
Soluzione premiscelata COV:	35 g/l
Categoria COV:	IIA/d
Limite di COV:	130g/l (2010.)
Note riguardanti la sicurezza:	Consult Safety Data Sheet and Safety Information printed on the can.

## SCADENZA

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Data del rilascio: 07/02/2025

**Colori e formati di confezione disponibili:** Si prega di consultare la pagina relativa al prodotto su [www.rust-oleum.eu](http://www.rust-oleum.eu) per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

**Dichiarazione di non responsabilità:** Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da [www.rust-oleum.eu](http://www.rust-oleum.eu) o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu