



PARAFIX[®]

Fixating and impregnating primer

- Parafix[®] is a special impregnating primer for roofing and bituminous products, before recoating with Dacfill
- It is also used as a primer under Paracent[®].
- Parafix[®] is a milky liquid which becomes colourless after drying
- It prevents the absorption of waterborne paints on porous substrates

POPIS PRODUKTU (DLHÝ)

Colourless fixation primer based on acrylic dispersions for weathered bituminous substrates. It prevents the absorption of waterborne paints on porous substrates.

ODPORÚČANÉ POUŽITIE

Fixation coat on weathered bituminous surfaces before recoating with Dacfill, Dacfill HZ or Dac-Hydro-Alu.

TECHNICAL DATA

| | |
|----------------------------------|-------------|
| Hustota (g/cm ³): | 1,0 |
| Úroveň lesku: | Gloss |
| Úroveň lesku pri 60°: | Glossy: 90% |
| Obsah pevných látok v hmotnosti: | 27 - 29% |
| Obsah pevných látok v objeme: | 27 - 29 % |

DRY TIMES BY 20

| | |
|-------------------------------|-----------|
| Na dotyk suché: | 1,5 hours |
| Suché na manipuláciu: | 4 hours |
| Suchý na opätovné natieranie: | 1 day |
| Úplne vytvrdnuté: | 1 week |

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

28 µm

TEORETICKÁ SPOTREBA

5 - 10 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Do not apply on fibre cement boards: use Primer 44 HS in this case.
Do not apply on low porous substrates like plaster, use Pegafix in this case.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

> 5°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted.

APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Apply undiluted.

Nozzle: 011 - 015 / Pressure: 180 - 200 bars

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Dilute with water.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

DATA SAFETY DATA

| | |
|-------------------------|--|
| Úroveň VOC: | 40 g/l |
| VOC ready mix: | 40 g/l |
| Kategória VOC: | A/i |
| Limit VOC: | 140 g/l |
| Poznámky k bezpečnosti: | Consult Safety Data Sheet and Safety Information printed on the can. |

SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu