

Quality Paints since 1845
MATHYS[®]



PARASIL COMPACT

High build intermediate coat, siloxane resins

- Waterborne acrylic and polysiloxane resin
- Very thick coat with high covering power
- Application in 1 or 2 coats
- Direct application on well adhering, solid, even and uneven substrates
- Masks haircracking

PARASIL COMPACT

POPIS PRODUKTU (DLOUHÝ)

High build priming and intermediate coat based on waterborne acrylic and polysiloxane resins. To be used in combination with ParaSil®.

DOPORUČENÉ POUŽITÍ

High build priming and intermediate coat for the protection and decoration of new or old exterior walls. Walls in masonry, concrete, hydraulic plasters. Masks hair-line cracking. Maintenance of old elastic paint coats and outer wall insulation.

DOPORUČENÝ SYSTÉM

On bare substrates or old well adhering and compatible undercoats: 1 coat of Parasil Compact: 500 to 700 g/m² plus 1 or 2 top coats of Parasil.
On very porous substrates: pretreatment with Primer 44 HS – 10 m²/l. Irregular surfaces: levelling with Pegacrete or with a suitable filler.

TECHNICAL DATA

Hustota (g/cm³): 1,54
Úroveň lesku: Matt
Obsah pevných látek v hmotnosti: 67 - 69 %
Obsah pevných látek v objemu: 49 - 51 %

DRY TIMES BY 20

Dotykem suché: 4 hours
Suchý nátěr: 24 hours

PRAKTICKÁ SPOTŘEBA

PŘÍPRAVA POVRCHU

The substrate must be completely clean, dry and solid. In case of contamination by microorganisms the substrate must first be cleaned with a fungicide solution.

NÁVOD K POUŽITÍ

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

The works must be performed in conformity with DTU 59-1. Minimum temperature 7°C, maximum 30 °C and maximum relative humidity 80%.
No condensation during drying time. Low temperatures and/or high relative humidity will extend the drying time. Do not apply on hot walls and in direct sunlight.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Synthetic brushes for water dilutable paints

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Polyamide rollers with 20 mm long hair or longer according to roughness.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

DATA SAFETY DATA

Úroveň těkavých organických látek: 35 g/l
VOC readymix: 35 g/l
Kategorie VOC: A/c
Limitní hodnota VOC: 40 g/l
Poznámky k bezpečnosti: Consult safety data sheet and Safety information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 1 year from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 7° and 30°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu