



PARASIL

A high build matt silanized wall paint

- Mineral-like matt aspect
- Durable
- Low odour
- Dirt and water repellent
- Low stress

PARASIL

POPIS PRODUKTU (DLOUHÝ)

ParaSil® is a high build matt silanized wall paint. Based on siloxane resins and 100% acrylic resins. Suitable for uneven, structured substrates.

DOPORUČENÉ POUŽITÍ

Mineral matt finish for exterior walls. Can be applied on most mineral substrates and old dispersion paints. Suitable for uneven structured substrates. No cracking in deeper areas of the treated substrate (e.g. brick).

TECHNICAL_DATA

Hustota (g/cm ³):	1,47 - 1,51 (wit)
Úroveň lesku:	Matt
Obsah pevných látek v hmotnosti:	68,5 - 70,5 % (wit)
Obsah pevných látek v objemu:	52,5 - 54,5 % (wit)

DRY_TIMES_BY_20

Dotykem suché:	2-3 hours
Suchý nátěr:	12 hours
Plně vytvrzené:	1 day

TEORETICKÁ SPOTŘEBA

5 - 7 m²/l per coat

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

PŘÍPRAVA POVRCHU

Old cleaned layers in good condition and light porous substrates (such as concrete, cement, plaster, etc.) can be recoated directly with ParaSil. Strongly porous substrates and smooth plaster must first be impregnated with a coat of Pegafix Color EXT.

NÁVOD K POUŽITÍ

Substrate must be sufficiently dry and stable, and well cleaned. Previously cleaned old coatings in good condition and slightly porous and homogeneous substrates can be directly coated with Parasil or with high filling undercoat Parasil Compact in case of uneven surface. Very porous substrates or smooth renderings or water resistant plasters will be previously impregnated with Pegaprim Exterior. To block stains, graffiti and/or very fast recoating on any substrate, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain.

PODMÍNKY POUŽITÍ

> 10°C, < 80% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Do not dilute.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Do not dilute.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 013 - 019 / Pressure: 160 - 200 bar.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

DATA_SAFETY_DATA

Úroveň těkavých organických látek:	23 g/l
VOC readymix:	23 g/l
Kategorie VOC:	IIA/c
Limitní hodnota VOC:	40 g/l
Poznámky k bezpečnosti:	Consult safety data sheet and Safety information printed on the can.

DOBA POUŽITELNOSTI

At least 1 year from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 7° and 30°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu