



## PEGACRYL® SATIN

# Waterbased satingloss acrylic lacquer

- Weather resistance better than most synthetic enamels
- Good flow
- Good filling power
- High covering capacity

# PEGACRYL® SATIN

## POPIS PRODUKTU (DLOUHÝ)

Waterbased satingloss acrylic lacquer.

## DOPORUČENÉ POUŽITÍ

Woodwork, both inside and outside. As topcoat on Noxyde.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,25 - 1,32
Úroveň lesku:	Satin
Úroveň lesku při 60°:	Satin gloss: 30%
Obsah pevných látek v hmotnosti:	47 - 51 %
Obsah pevných látek v objemu:	31 - 34 %

## DRY TIMES BY 20

Dotykem suché:	1 hour
Suché na manipulaci:	5 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	2 days

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

35 µm

## TEORETICKÁ SPOTŘEBA

9 - 12 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Painted substrates: apply directly on old sound paints; glossy paints will be roughed up slightly. Untreated substrates: on woodwork, apply a coat of Fassiprim Aqua XPE. Block wood knots and sap streaks with Zinsser primer B-I-N. For stain, graffiti blocking and/or very fast recoating, use Zinsser primers Bulls Eye 123 or 123 Plus.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

> 10°C, < 80% H.R.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Do not dilute.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Do not dilute.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 018 / Pressure: 180 bars.

If required dilute with some water.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Dilute with water.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

## POZNÁMKY

Apply Pegacryl Satin by preference by airless or brush.

Do not apply in full sun or too hot conditions, to avoid a decreased flow.

## DATA SAFETY DATA

Úroveň těkavých organických

látek: 128 g/l

VOC readymix: 128 g/l

Kategorie VOC: A/d

Limitní hodnota VOC: 130 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5 and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chiène  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu