



PEGACRYL® SATIN

Waterbased satingloss acrylic lacquer

- Weather resistance better than most synthetic enamels
- Good flow
- Good filling power
- High covering capacity

PEGACRYL® SATIN

POPIS PRODUKTU (DLHÝ)

Waterbased satingloss acrylic lacquer.

ODPORÚČANÉ POUŽITIE

Woodwork, both inside and outside. As topcoat on Noxyde.

TECHNICAL DATA

Hustota (g/cm ³):	1,25 - 1,32
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	Satin gloss: 30%
Obsah pevných látok v hmotnosti:	47 - 51 %
Obsah pevných látok v objeme:	31 - 34 %

DRY TIMES BY 20

Na dotyk suché:	1 hour
Suché na manipuláciu:	5 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdnuté:	2 days

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

35 µm

TEORETICKÁ SPOTREBA

9 - 12 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Painted substrates: apply directly on old sound paints; glossy paints will be roughed up slightly. Untreated substrates: on woodwork, apply a coat of Fassiprim Aqua XPE. Block wood knots and sap streaks with Zinsser primer B-I-N. For stain, graffiti blocking and/or very fast recoating, use Zinsser primers Bulls Eye 123 or 123 Plus.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

> 10°C, < 80% H.R.

APLIKÁCIA A RIEDENIE: ŠTETEC

Do not dilute.

APLIKÁCIA A RIEDENIE: VALEC

Do not dilute.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 018 / Pressure: 180 bars.

If required dilute with some water.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Dilute with water.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

POZNÁMKY

Apply Pegacryl Satin by preference by airless or brush.

Do not apply in full sun or too hot conditions, to avoid a decreased flow.

DATA SAFETY DATA

Úroveň VOC:	128 g/l
VOC ready mix:	128 g/l
Kategória VOC:	A/d
Limit VOC:	130 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5 and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu