

Quality Paints since 1845
MATHYS[®]



PEGACRYL[®] SATIN

Waterbased satingloss acrylic lacquer

- Weather resistance better than most synthetic enamels
- Good flow
- Good filling power
- High covering capacity

PEGACRYL® SATIN

BESKRIVNING

Waterbased satingloss acrylic lacquer.

REKOMMENDERAD ANVÄNDNING

Woodwork, both inside and outside. As topcoat on Noxyde.

TEKNISK DATA

Densitet:	1,25 - 1,32
Glansnivå:	Satin
Glansnivå vid 60°:	Satin gloss: 30%
Torrsubstansvikt:	47 - 51 %
Torrsubstansvolym:	31 - 34 %

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour
Hanteringstorr:	5 hours
Övermålningsbar:	24 hours
Fullt härdad:	2 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

35 µm

TEORETISK FÖRBRUKNING

9 - 12 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

Painted substrates: apply directly on old sound paints; glossy paints will be roughed up slightly. Untreated substrates: on woodwork, apply a coat of Fassiprim Aqua XPE. Block wood knots and sap streaks with Zinsser primer B-I-N. For stain, graffiti blocking and/or very fast recoating, use Zinsser primers Bulls Eye 123 or 123 Plus.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

> 10°C, < 80% H.R.

APPLICERING OCH SPÄDNING: PENSEL

Do not dilute.

APPLICERING OCH SPÄDNING: ROLLER

Do not dilute.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Nozzle: 018 / Pressure: 180 bars.
If required dilute with some water.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Dilute with water.

RENGÖRING AV UTRUSTNING/SPILL

Water.

ANMÄRKNINGAR

Apply Pegacryl Satin by preference by airless or brush.
Do not apply in full sun or too hot conditions, to avoid a decreased flow.

SÄKERHETSDATA

VOC-nivå:	128 g/l
VOC färdigmix:	128 g/l
VOC-kategori:	A/d
VOC-gräns:	130 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5 and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europas rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu