



Quality Paints since 1845
MATHYS®



PEGAFLEX®

Levelling filler based on acrylic resins dispersed in water

- High flexibility and elasticity
- Excellent adhesion on all sound substrates and paints
- Perfect alkali resistant
- Not affected by ageing thus keeping its original flexibility
- Sufficiently hard, but can still be sanded easily



PEGAFLEX®

POPIS PRODUKTU (DLHÝ)

Levelling filler based on acrylic resins dispersed in water.

ODPORÚČANÉ POUŽITIE

For indoor and outdoor works; can be used on any non-powdering substrates.

TECHNICAL DATA

Hustota (g/cm ³):	± 1,8
Úroveň lesku:	Matt
Úroveň lesku pri 60°:	Matt: 3%
Obsah pevných látok v hmotnosti:	78 - 80 %
Obsah pevných látok v objeme:	61 - 64 %

DRY TIMES BY 20

Na dotyk suché:	3 hours
Suché na manipuláciu:	8 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrnuté:	2 days

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

1000 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

630 µm

TEORETICKÁ SPOTREBA

Max. 1,8 kg/m² (= 1 mm thick)

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Fill up deep holes with a filler or with a repair mortar (Pegacrete).
Chalking substrates must be primed with Fixonal.
Porous mineral substrates have to be pre-treated with Pegafix.
Bare wood should be impregnated with Adex first.
If you want to recoat with an acrylic paint, you should isolate the filled up parts with Porisol first. If it is necessary to get a thick layer, you should apply several layers after hardening of the previous layer.

NÁVOD NA POUŽITIE

Use a filling knife and apply thin layers.

PODMIENKY APLIKÁCIE

> 5°C, < 80% R.H.

ČISTENIE ZARIADENIA / POSTRIEKANIE

With water as long as Pegaflex has not dried; when dry clean with Thinner 22.

POZNÁMKY

Pegaflex can easily be sanded wet, but not dry.

DATA SAFETY DATA

Úroveň VOC:	30 g/l
VOC ready mix:	30 g/l
Kategória VOC:	A/i
Limit VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu