

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



**PEGALINK<sup>®</sup>**

## Universal adhesion primer

- Excellent adhesion on a lot of surfaces
- Flexible
- Excellent flow
- UV-resistant

## POPIS PRODUKTU (DLOUHÝ)

Universal adhesion primer based on water dispersed acrylic resins.

## DOPORUČENÉ POUŽITÍ

Adhesion on a lot of surfaces: wood, gypsum, cement, bricks and especially on smooth and difficult to adhere to surfaces like: galvanized steel, copper, zinc, polycarbonate, hard PVC, Pegagraff Hydro, etc. Can be used in- and outdoors.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,2 - 1,3
Úroveň lesku:	Satin
Úroveň lesku při 60°:	Satin: ± 20%
Obsah pevných látek v hmotnosti:	± 52 %
Obsah pevných látek v objemu:	± 37 %

## DRY TIMES BY 20

Dotykem suché:	20 minutes
Suché na manipulaci:	1 hour
Suchý nátěr:	24 hours with waterborne paints. Decorative alkyd lacquers should be checked first by means of an adhesion test.
Plně vytvrzené:	2 days

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

36 µm

## TEORETICKÁ SPOTŘEBA

± 10 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

In general, it is not necessary to mat smooth surfaces by sanding; in most cases cleaning and/or degreasing of the surface is sufficient in order to obtain good adhesion.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

> 5°C, < 80% R.H.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

All types can be used. Do not dilute.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Not recommended, except with a lacquer roller. Do not dilute

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 11 / Pressure: 200 bars. Do not dilute.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Possible, do not dilute.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

## POZNÁMKY

Adhesion cross-cut intact on the above-mentioned surfaces.

In case of doubt, f.i. on a substrate which has not been mentioned, an adhesion test has to be done after 2 days of drying, especially on old paints.

## DATA SAFETY DATA

Úroveň těkavých organických látek:	45 g/l
VOC readymix:	45 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu