

Quality Paints since 1845
MATHYS[®]



PEGALINK[®]

Universal adhesion primer

- Excellent adhesion on a lot of surfaces
- Flexible
- Excellent flow
- UV-resistant

POPIS PRODUKTU (DLHÝ)

Universal adhesion primer based on water dispersed acrylic resins.

ODPORÚČANÉ POUŽITIE

Adhesion on a lot of surfaces: wood, gypsum, cement, bricks and especially on smooth and difficult to adhere to surfaces like: galvanized steel, copper, zinc, polycarbonate, hard PVC, Pegagraff Hydro, etc. Can be used in- and outdoors.

TECHNICAL DATA

Hustota (g/cm ³):	1,2 - 1,3
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	Satin: ± 20%
Obsah pevných látok v hmotnosti:	± 52 %
Obsah pevných látok v objeme:	± 37 %

DRY TIMES BY 20

Na dotyk suché:	20 minutes
Suché na manipuláciu:	1 hour
Suchý na opätovné natieranie:	24 hours with waterborne paints. Decorative alkyd lacquers should be checked first by means of an adhesion test.
Úplne vytvrdené:	2 days

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

36 µm

TEORETICKÁ SPOTREBA

± 10 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

In general, it is not necessary to mat smooth surfaces by sanding; in most cases cleaning and/or degreasing of the surface is sufficient in order to obtain good adhesion.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

> 5°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

All types can be used. Do not dilute.

APLIKÁCIA A RIEDENIE: VALEC

Not recommended, except with a lacquer roller. Do not dilute

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 11 / Pressure: 200 bars. Do not dilute.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Possible, do not dilute.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

POZNÁMKY

Adhesion cross-cut intact on the above-mentioned surfaces.

In case of doubt, f.i. on a substrate which has not been mentioned, an adhesion test has to be done after 2 days of drying, especially on old paints.

DATA SAFETY DATA

Úroveň VOC:	45 g/l
VOC readymix:	45 g/l
Kategória VOC:	A/i
Limit VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu