



Quality Paints since 1845
MATHYS®



PEGAMAT® AQUA ISOLE

Low tension stain blocking renovation paint

- Low tension film
- Primer and topcoat in one
- Insulates nicotine and smoke stains, old damp spots and numerous colorants
- Long open time
- Quickly recoatable

PEGAMAT® AQUA ISOLE

POPIS PRODUKTU (DLOUHÝ)

Water based low tension matt renovation and stain blocking paint for use on interior walls and ceilings based on modified alkyl resins.

DOPORUČENÉ POUŽITÍ

Low tension renovation paint for interior walls and ceilings.

TECHNICAL_DATA

Hustota (g/cm ³):	1,45 - 1,51
Úroveň lesku:	Matt
Úroveň lesku při 85°:	Matt: 2%
Obsah pevných látek v hmotnosti:	58 - 62 % (weiss)
Obsah pevných látek v objemu:	38 - 42 % (weiss)

DRY_TIMES_BY_20

Dotykem suché:	1 hour
Suchý nátěr:	2 hour
Plně vytvrzené:	2 days

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

140 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

56 µm

TEORETICKÁ SPOTŘEBA

7 m²/l per coat

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc.

Apply on a dry and sound substrate. Apply 1 or 2 coats according to the condition of the substrate.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat Aqua Isole.

On very absorbent substrates (not painted), apply an impregnation coat of Pegafix.

On substrates with nicotine spots: first clean these with an ammonia solution in order to receive a better efficiency of the paint.

Can be applied on completely dry Elastofill/Pegaflex without the risk of crack formation.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

> 5°C, < 80% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 011 - 013 / Pressure: 180 bar.

If necessary, dilute with a little water.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

If necessary, dilute with a little water.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

POZNÁMKY

Apply a preliminary test patch in case of old damp spots and colour marks. When insulation properties are insufficient, use Pegamat RL Isole or Pegaprim Isofix.

Can be applied directly on Pegamat RL Isole, Pegaprim Isofix and Pegaprim Xpress.

Can be recoated with all water-based paint, and also with Pegamat RL Isole.

DATA_SAFETY_DATA

Úroveň těkavých organických

látek: 53 g/l

VOC readymix: 53 g/l

Kategorie VOC: A/i

Limitní hodnota VOC: 140 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu