

Quality Paints since 1845
MATHYS[®]



PEGAMAT[®] AQUA ISOLE

Low tension stain blocking renovation paint

- Low tension film
- Primer and topcoat in one
- Insulates nicotine and smoke stains, old damp spots and numerous colorants
- Long open time
- Quickly recoatable

PEGAMAT® AQUA ISOLE

BESKRIVELSE

Water based low tension matt renovation and stain blocking paint for use on interior walls and ceilings based on modified alkyl resins.

ANBEFALT BRUK

Low tension renovation paint for interior walls and ceilings.

TEKNISKE DATA

Tetthet:	1,45 - 1,51
Glansgrad:	Matt
Glansgrad ved 85°:	Matt: 2%
Tørrestoffinnhold i vekt:	58 - 62 % (weiss)
Tørrestoffinnhold i volum:	38 - 42 % (weiss)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 hour
Overmalbar:	2 hour
Herdetid:	2 days

ANBEFALT VÅTFILMTYKKELSE

140 µm

ANBEFALT TØRRFILMTYKKELSE

56 µm

TEORETISK FORBRUK

7 m²/l per coat

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc.

Apply on a dry and sound substrate. Apply 1 or 2 coats according to the condition of the substrate.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat Aqua Isole.

On very absorbent substrates (not painted), apply an impregnation coat of Pegafix.

On substrates with nicotine spots: first clean these with an ammonia solution in order to receive a better efficiency of the paint.

Can be applied on completely dry Elastofill/Pegaflex without the risk of crack formation.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

> 5°C, < 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply undiluted.

PÅFØRING & FORTYNNING: RULLE

Apply undiluted.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 011 - 013 / Pressure: 180 bar.

If necessary, dilute with a little water.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

If necessary, dilute with a little water.

RENGJØRING AV UTSTYR/SPILL

Water.

MERKNADER

Apply a preliminary test patch in case of old damp spots and colour marks. When insulation properties are insufficient, use Pegamat RL Isole or Pegaprim Isofix.

Can be applied directly on Pegamat RL Isole, Pegaprim Isofix and Pegaprim Xpress.

Can be recoated with all water-based paint, and also with Pegamat RL Isole.

SIKKERHETSDATA

VOC nivå:	53 g/l
VOC ferdigblandet:	53 g/l
VOC kategori:	A/i
VOC grense:	140 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu