



Quality Paints since 1845
MATHYS®



PEGAMAT® RL ISOLE

Low tension renovation and stain blocking paint

- Good covering power
- Low odour
- Non yellowing
- Low tension film
- Unsaponifiable

PEGAMAT® RL ISOLE

BESKRIVELSE

Deodorised low tension solvent-based insulating or blocking paint based on plastified acrylic resins.

ANBEFALT BRUK

Low tension renovation paint for interior walls and ceilings.

TEKNISKE DATA

Tetthet:	1.33 - 1.37 g/cm ³
Glansgrad:	Matt
Glansgrad ved 60°:	Matt: < 2%
Tørrestoffinnhold i vekt:	64 - 66%
Tørrestoffinnhold i volum:	38 - 40%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	3 h
Overmalbar:	Wet in wet or after 4 h
Herdetid:	1 day

ANBEFALT VÅTFILMTYKKELSE

100 µm

ANBEFALT TØRRFILMTYKKELSE

40 µm

TEORETISK FORBRUK

9 - 12 m²/l per coat

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc. Substrates should be sufficiently dry and stable. Apply 1 or 2 coats according to the condition of the substrate; if necessary, the second coat can be applied wet in wet. Do not apply on Elastofill; when using Pegaflex, it must first be insulated with Porisol.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat RL Isole.

Very porous substrates are to be impregnated first with Pegafix.

Persistent stains are to be treated with Pegaprim® Isofix.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

Dilute with 3-5% Thinner RL or White spirit if necessary.

PÅFØRING & FORTYNNING: RULLE

Dilute with 3-5% Thinner RL or White spirit if necessary.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 011 - 015 / Pressure: 180 bars.

Dilute max. 5% with Thinner RL or White spirit if necessary.

PÅFØRING & FORTYNNING: FORSTØVNINGS-SPRØYTE

Possible.

RENGJØRING AV UTSTYR/SPILL

White spirit.

MERKNADER

White spirit increases the odour and makes its use impossible on polystyrene foam.

Pegamat RL Isole is a reversible paint system, this means that it dissolves in its own solvent. Therefore, dried spots of Pegamat RL Isole can be removed with Thinner RL or white spirit. Do not tint with universal pigments or on the tinting machine.

SIKKERHETSDATA

VOC nivå:	455 g/l
VOC ferdigblandet:	485 g/l
VOC kategori:	A/i
VOC grense:	500 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu