



Quality Paints since 1845  
**MATHYS®**



## PEGAPRIM® EXTERIOR

### Water-based primer

- Reinforces the substrate and reduces absorption
- Neutralises differences in absorption characteristics
- Prevents differences in the glossiness of the topcoat
- Very good hiding characteristics
- Improves topcoat adhesion

# PEGAPRIM® EXTERIOR

## BESKRIVELSE

Water-based primer based on acrylic dispersions. Neutralises differences in the absorption characteristics of the substrate. Provides a substrate with uniform absorption and colour.

## ANBEFALT BRUK

Acrylate primer for exterior applications. Can be applied to most mineral substrates

## TEKNISKE DATA

Tetthet:	± 1,35 (weiss)
Glansgrad:	Matt
Glansgrad ved 60°:	Matt: ± 5%
Tørrestoffinnhold i vekt:	58 % (weiss)
Tørrestoffinnhold i volum:	45 % (weiss)

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtør:	1,5 hours
Overmalbar:	2-3 hours
Herdetid:	1 week

## ANBEFALT VÅTFILMTYKKELSE

100 µm

## ANBEFALT TØRRFILMTYKKELSE

45 µm

## TEORETISK FORBRUK

± 8 - 10 m<sup>2</sup>/l

## PRAKTISK FORBRUK

Depends on several factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

## KLARGJØRING AV OVERFLATE

The substrate should be dry, clean and free of grease. Pegaprim Exterior may be directly applied over normally porous substrates and old, cleaned paint layers if they are in good condition. Not suitable for highly porous substrates; use Pegafix as a fixator in such cases.

## BRUKSANVISNING

The product should be thoroughly stirred before use, to ensure homogeneity.

## PÅFØRINGSBETINGELSER

> 5°C, < 80% R.H.

## PÅFØRING & FORTYNNING: PENSEL

Use undiluted.

## PÅFØRING & FORTYNNING: RULLE

Use undiluted.

## PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 011 - 015 / Pressure: 180 - 200 bar.

Apply undiluted.

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Use undiluted.

## RENGJØRING AV UTSTYR/SPILL

Water.

## SIKKERHETSDATA

VOC nivå:	30 g/l
VOC ferdigblandet:	30 g/l
VOC kategori:	A/g
VOC grense:	30 g/l
Merknader angående sikkerhet:	Refer to the Product Data Sheet and the information on the packaging.

## HOLDBARHET

At least 2 years from manufacturing date, if stored in the unopened, original packaging in dry, well-ventilated areas, not in direct sunlight, and at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukeren er selv ansvarlig for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu