



Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## PEGAPRIM<sup>®</sup> EXTERIOR

### Water-based primer

- Reinforces the substrate and reduces absorption
- Neutralises differences in absorption characteristics
- Prevents differences in the glossiness of the topcoat
- Very good hiding characteristics
- Improves topcoat adhesion

# PEGAPRIM® EXTERIOR

## POPIS PRODUKTU (DLHÝ)

Water-based primer based on acrylic dispersions. Neutralises differences in the absorption characteristics of the substrate. Provides a substrate with uniform absorption and colour.

## ODPORÚČANÉ POUŽITIE

Acrylate primer for exterior applications. Can be applied to most mineral substrates

## TECHNICAL\_DATA

Hustota (g/cm <sup>3</sup> ):	± 1,35 (weiss)
Úroveň lesku:	Matt
Úroveň lesku pri 60°:	Matt: ± 5%
Obsah pevných látok v hmotnosti:	58 % (weiss)
Obsah pevných látok v objeme:	45 % (weiss)

## DRY\_TIMES\_BY\_20

Na dotyk suché:	1,5 hours
Suchý na opätovné natieranie:	2-3 hours
Úplne vytvrdené:	1 week

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

45 µm

## TEORETICKÁ SPOTREBA

± 8 - 10 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Depends on several factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

## PRÍPRAVA POVRCHU

The substrate should be dry, clean and free of grease. Pegaprim Exterior may be directly applied over normally porous substrates and old, cleaned paint layers if they are in good condition. Not suitable for highly porous substrates; use Pegafix as a fixator in such cases.

## NÁVOD NA POUŽITIE

The product should be thoroughly stirred before use, to ensure homogeneity.

## PODMIENKY APLIKÁCIE

> 5°C, < 80% R.H.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Use undiluted.

## APLIKÁCIA A RIEDENIE: VALEC

Use undiluted.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 011 - 015 / Pressure: 180 - 200 bar.

Apply undiluted.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Use undiluted.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

## DATA\_SAFETY\_DATA

Úroveň VOC:	30 g/l
VOC readymix:	30 g/l
Kategória VOC:	A/g
Limit VOC:	30 g/l
Poznámky k bezpečnosti:	Refer to the Product Data Sheet and the information on the packaging.

## SKLADOVATELNOSŤ

At least 2 years from manufacturing date, if stored in the unopened, original packaging in dry, well-ventilated areas, not in direct sunlight, and at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu