



Quality Paints since 1845  
**MATHYS®**



## PEGAPRIM® XPRESS

# Fast drying universal and stain block primer

- Quick drying
- Flexible/insulating
- Good filling and hiding power
- Closed good adhering paint film
- Recoatable with most water and solvent borne decorative paints

# PEGAPRIM® XPRESS

## POPIS PRODUKTU (DLHÝ)

Insulating and fast drying universal adhesion primer based on water borne acrylic resins.

## ODPORÚČANÉ POUŽITIE

For inside and outside.

Adhesion on metal (steel, zinc, aluminium, galvanised steel) and on smooth hard surfaces (PVC, polyester, Formica). Closes porous substrates (masonry, plaster rendering, concrete, wood, fibreboards).

Insulates spots (tar, soot, graffiti, humidity); in difficult circumstances use Pegaprim Isofix.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	± 1,26
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	Satin gloss: ± 15%
Obsah pevných látok v hmotnosti:	± 52 %
Obsah pevných látok v objeme:	± 39 %

## DRY TIMES BY 20

Na dotyk suché:	30 minutes
Suchý na opätovné natieranie:	1 hour
Úplne vytvrdené:	2 days

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

40 µm

## TEORETICKÁ SPOTREBA

± 10 m<sup>2</sup>/l per coat

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

## PRÍPRAVA POVRCHU

The surface should be clean, dry and stable.

Where necessary, degrease.

Contamination has to be removed as thoroughly as possible.

Reinforce the wood structure if necessary (e.g. after burning off of new wood on the outside) by impregnating with Adex.

Wood knots have to be insulated beforehand with Pegapim Isofix.

Old intact lacquer paint coats should be roughened up slightly in order to assure an optimal adhesion.

In case of doubt, realise an adhesion test.

When applied as spot insulator, a longer drying time should be respected before recoating.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

> 5°C, < 80% R.H.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Apply preferably undiluted.

## APLIKÁCIA A RIEDENIE: VALEC

Apply preferably undiluted.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 0,011 - 0,013 inch / Pressure: 200 bars.

If necessary, dilute with water.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Dilute with a few % volume of water.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

## DATA SAFETY DATA

Úroveň VOC:	40 g/l
VOC readymix:	40 g/l
Kategória VOC:	A/g
Limit VOC:	30 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chiène  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu