

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## PEGAPRIM<sup>®</sup> XPRESS

### Fast drying universal and stain block primer

- Quick drying
- Flexible/insulating
- Good filling and hiding power
- Closed good adhering paint film
- Recoatable with most water and solvent borne decorative paints

# PEGAPRIM® XPRESS

## BESKRIVNING

Insulating and fast drying universal adhesion primer based on water borne acrylic resins.

## REKOMMENDERAD ANVÄNDNING

For inside and outside.

Adhesion on metal (steel, zinc, aluminium, galvanised steel) and on smooth hard surfaces (PVC, polyester, Formica). Closes porous substrates (masonry, plaster rendering, concrete, wood, fibreboards).

Insulates spots (tar, soot, graffiti, humidity); in difficult circumstances use Pegaprim Isofix.

## TEKNISK DATA

Densitet:	± 1,26
Glansnivå:	Satin
Glansnivå vid 60°:	Satin gloss: ± 15%
Torrsubstansvikt:	± 52 %
Torrsubstansvolym:	± 39 %

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	30 minutes
Övermålningsbar:	1 hour
Fullt härdad:	2 days

## REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm

## REKOMMENDERAD TORRFILMSTJOCKLEK

40 µm

## TEORETISK FÖRBRUKNING

± 10 m<sup>2</sup>/l per coat

## PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

## YTFÖRBEREDELSE

The surface should be clean, dry and stable.

Where necessary, degrease.

Contamination has to be removed as thoroughly as possible.

Reinforce the wood structure if necessary (e.g. after burning off of new wood on the outside) by impregnating with Adex.

Wood knots have to be insulated beforehand with Pegaprim Isofix.

Old intact lacquer paint coats should be roughened up slightly in order to assure an optimal adhesion.

In case of doubt, realise an adhesion test.

When applied as spot insulator, a longer drying time should be respected before recoating.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICERINGSFÖRHÅLLANDEN

> 5°C, < 80% R.H.

## APPLICERING OCH SPÅDNING: PENSEL

Apply preferably undiluted.

## APPLICERING OCH SPÅDNING: ROLLER

Apply preferably undiluted.

## APPLICERING OCH SPÅDNING: AIRLESSPRUTA

Nozzle: 0,011 - 0,013 inch / Pressure: 200 bars.

If necessary, dilute with water.

## APPLICERING OCH SPÅDNING: TRYCKLUFTSSPRUTA

Dilute with a few % volume of water.

## RENGÖRING AV UTRUSTNING/SPILL

Water.

## SÄKERHETSDATA

VOC-nivå:	40 g/l
VOC färdigmix:	40 g/l
VOC-kategori:	A/g
VOC-gräns:	30 g/l
Anmärkingar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)