

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



**PEGATEX<sup>®</sup>**

**Latex paint for interior and exterior protection.**

- Mat appearance
- Easy cleanability
- Easy to apply
- Good hiding

## POPIS PRODUKTU (DLHÝ)

Latex paint for interior and exterior protection.

## ODPORÚČANÉ POUŽITIE

Interior walls: plaster, rendering, fibre cement panels, Gyproc. Exterior walls: bricks, all kinds of construction materials except new ones less than 2 years old.

## TECHNICAL\_DATA

|  |          |
|--|----------|
| Hustota (g/cm <sup>3</sup> ):              | ± 1,4    |
| Úroveň lesku:                              | Matt     |
| Úroveň lesku pri 60°:                      | Matt: 2% |
| Obsah pevných látok v hmotnosti:           | ± 58 %   |
| Obsah pevných látok v objeme:              | ± 39,5 % |
| Odolnosť voči mokrému drhnutiu (EN 13300): | wsr_c1   |

## DRY\_TIMES\_BY\_20

|                               |         |
|-------------------------------|---------|
| Na dotyk suché:               | 1 hour  |
| Suché na manipuláciu:         | 5 hours |
| Suchý na opätovné natieranie: | 4 hours |
| Úplne vytvrdené:              | 1 day   |

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

37 µm

## TEORETICKÁ SPOTREBA

8 - 10 m<sup>2</sup>/l per coat

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

## PRÍPRAVA POVRCHU

Application on not alkaline substrates in good state.

Interior: porous surfaces to prime with Pegafix or with a first coat diluted with 10% volume water.

Exterior: Not painted substrates to prime with Pegafix.

Old water or nicotine stains must be blocked with Pegamat® RL or Zinsser primers Bulls-Eye 123 ou 123 Plus.

## NÁVOD NA POUŽITIE

Before application, stir the product till completely homogenous.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Do not dilute.

## APLIKÁCIA A RIEDENIE: VALEC

Do not dilute.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

If necessary, dilute with water.

Nozzle: 013/ Pressure: 180 bar.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

If necessary, dilute with water.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

## DATA SAFETY\_DATA

|                         |  |
|-------------------------|--|
| Úroveň VOC:             | 20 g/l   |
| VOC readymix:           | 29.8 g/l   |
| Kategória VOC:          | A/a  |
| Limit VOC:              | 30 g/l   |
| Poznámky k bezpečnosti: | Consult Safety Data Sheet and Safety Information printed on the can. |

## SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu