

Quality Paints since 1845
MATHYS[®]



PLASTI-PARKET

Parquet floor protection

- Simple to use
- Air-drying
- Excellent resistance against abrasion
- Makes maintenance easier
- Suitable for spot repairs



PLASTI-PARKET

POPIS PRODUKTU (DLOUHÝ)

Solvent-based varnish based on a modified polyurethane alkyd binder.

DOPORUČENÉ POUŽITÍ

Treatment and protection of parquet floors and wooden staircases.

TECHNICAL DATA

Hustota (g/cm ³):	0,90 - 0,92
Úroveň lesku:	Satin
Úroveň lesku při 60°:	Semi gloss: ± 15%
Obsah pevných látek v hmotnosti:	52 - 54 %
Obsah pevných látek v objemu:	43 - 45 %

DRY TIMES BY 20

Dotykem suché:	1,5 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

40 µm

TEORETICKÁ SPOTŘEBA

± 10 m²/l per coat

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

New parquet floors or parquet floors rub down until bare wood: dedust thoroughly, impregnate with FassiForce and let dry for minimum one night. After this, rub down lightly. Remark: replace FassiForce with diluted Duritane Gloss if the wood is colored too strongly. Old parquet floors already treated with wax: first remove the wax layer thoroughly (scrape). Use cleaning cloths soaked with white spirit. After this, apply one coat FassiForce. The FassiForce layer should be completely dry the next day. If this is not the case, it is an indication that the old wax layer was not removed enough. Clean the floor again as described above.

Remark: use sufficient cleaning cloths to remove the wax layer in order to avoid that the removed wax is applied on other parts of the floor.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

If necessary dilute with maximum 5% volume white spirit or Thinner 22.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

If necessary dilute with maximum 5% volume white spirit or Thinner 22. Use a fine roller.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Not recommended.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit or Thinner 22.

POZNÁMKY

Mix Plasti-Parket during application in order to make sure that the product will stay homogeneous.

Apply minimum 2 coats of Plasti-Parket.

DATA SAFETY DATA

Úroveň těkavých organických látek:	445 g/l
VOC readymix:	466 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu