

Quality Paints since 1845
MATHYS[®]



PLASTOPAN SUPER N

Solvent-based synthetic filler

- Quick hardening
- Excellent filling
- Contains no water soluble substances
- absorbs very little of the applied paint

PLASTOPAN SUPER N

POPIS PRODUKTU (DLOUHÝ)

Solvent-based synthetic filler based on linseed oil alkylid resin.

DOPORUČENÉ POUŽITÍ

Smoothing out uneven areas in indoor and outdoor woodwork that have to be recoated with oil based or synthetic paints.

TECHNICAL_DATA

Hustota (g/cm³): ± 2,4
Úroveň lesku: Matt
Obsah pevných látek v hmotnosti: ± 87 %
Obsah pevných látek v objemu: ± 70 %

DRY_TIMES_BY_20

Dotykem suché: 1 hour
Suchý nátěr: 24 hours
Plně vytvrzené: 1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

± 2 mm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

± 1,4 mm

TEORETICKÁ SPOTŘEBA

1 - 5 kg/m²

PRAKTICKÁ SPOTŘEBA

Depends on several factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

PŘÍPRAVA POVRCHU

Clean the substrate thoroughly, remove old weather-stained paint that is adhering poorly. Apply a thin layer of Fassiprim (diluted with ± 10% volume white spirit) on surfaces before filling them.

First treat substrates that are powdering or chalking with Fixonal. After filling and sanding, apply a primer coat of Fassiprim on all the surfaces; if matt finished portions are still visible after the primer dries, re-apply the primer to obtain a uniform appearance.

NÁVOD K POUŽITÍ

Apply in a dry and well-ventilated environment.

PODMÍNKY POUŽITÍ

Apply in a dry and well ventilated environment.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit

POZNÁMKY

Apply thin layers of Plastopan Super N.

DATA_SAFETY_DATA

Úroveň těkavých organických látek:

390 g/l

Poznámky k bezpečnosti:

Consult Safety Data Sheet and Safety Information printed on the packaging.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production, if stored in the unopened, original packaging in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu