

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## PLASTOPAN SUPER N

### Solvent-based synthetic filler

- Quick hardening
- Excellent filling
- Contains no water soluble substances
- absorbs very little of the applied paint

# PLASTOPAN SUPER N

## POPIS PRODUKTU (DLHÝ)

Solvent-based synthetic filler based on linseed oil alkyd resin.

## ODPORÚČANÉ POUŽITIE

Smoothing out uneven areas in indoor and outdoor woodwork that have to be recoated with oil based or synthetic paints.

## TECHNICAL\_DATA

Hustota (g/cm<sup>3</sup>): ± 2,4  
Úroveň lesku: Matt  
Obsah pevných látok v hmotnosti: ± 87 %  
Obsah pevných látok v objeme: ± 70 %

## DRY\_TIMES\_BY\_20

Na dotyk suché: 1 hour  
Suchý na opätovné natieranie: 24 hours  
Úplne vytvrdené: 1 week

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

± 2 mm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

± 1,4 mm

## TEORETICKÁ SPOTREBA

1 - 5 kg/m<sup>2</sup>

## PRAKTICKÁ VÝDATNOSŤ

Depends on several factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

## PRÍPRAVA POVRCHU

Clean the substrate thoroughly, remove old weather-stained paint that is adhering poorly. Apply a thin layer of Fassiprim (diluted with ± 10% volume white spirit) on surfaces before filling them.

First treat substrates that are powdering or chalking with Fixonal. After filling and sanding, apply a primer coat of Fassiprim on all the surfaces; if matt finished portions are still visible after the primer dries, re-apply the primer to obtain a uniform appearance.

## NÁVOD NA POUŽITIE

Apply in a dry and well-ventilated environment.

## PODMIENKY APLIKÁCIE

Apply in a dry and well ventilated environment.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit

## POZNÁMKY

Apply thin layers of Plastopan Super N.

## DATA\_SAFETY\_DATA

Úroveň VOC: 390 g/l  
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the packaging.

## SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production, if stored in the unopened, original packaging in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu