



VERNAC GLOSS

Acrylic varnish

- Alkaliresistant
- Excellent flexibility
- High weather resistance
- Transparent
- Completely colourless

VERNAC GLOSS

POPIS PRODUKTU (DLOUHÝ)

Solvent based acrylic varnish.

DOPORUČENÉ POUŽITÍ

Protection of non-ferrous metals; renovation of transparent skylights (except for polycarbonate). Do not apply Vernac Gloss as floor varnish or on places that are subject to mechanical pressure.

TECHNICAL_DATA

Hustota (g/cm ³):	0,96 - 0,98
Úroveň lesku:	Gloss
Úroveň lesku při 60°:	Glossy: > 90%
Obsah pevných látek v hmotnosti:	47 - 49 %
Obsah pevných látek v objemu:	40 - 43 %

DRY_TIMES_BY_20

Dotykem suché:	1 hour
Suché na manipulaci:	1,5 hours
Suchý nátěr:	4 hours
Plně vytvrzené:	1 day

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

42 µm

TEORETICKÁ SPOTŘEBA

10 - 15 m²/l per coat

PRAKTIČKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

The substrates must be completely dry and clean. On metals, it is necessary to remove old varnish layers (with Rapid Super, for instance) and oxidation traces (with a polish, for instance). Clean afterwards with a cloth soaked in Thinner 22.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80%.

No condensation during drying time. Low temperatures and/or high relative humidity will extend the drying time. The temperature of the substrate should be 3°C above dew point.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

All types.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Mohair paint roller or short haired roller.

last_updated: 07/02/2025

ČIŠTĚní ZAŘÍZENÍ / ROZLITÍ

Thinner 22.

POZNÁMKY

2 - 3 coats for outside works.

DATA_SAFETY_DATA

Úroveň těkavých organických

látek:	499 g/l
VOC readymix:	499 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu