

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## VERNAC SATIN

### Acrylic varnish

- Alkaliresistant
- Excellent flexibility
- High weather resistance
- Transparent
- Completely colourless



# VERNAC SATIN

## POPIS PRODUKTU (DLOUHÝ)

Solvent based acrylic varnish.

## DOPORUČENÉ POUŽITÍ

Protection of non-ferrous metals. Renovation of transparent skylights (except for polycarbonate). Do not apply Vernac Satin as floor varnish or on places that are subject to mechanical pressure.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	0,99 - 1,01
Úroveň lesku:	Satin
Úroveň lesku při 60°:	Satin gloss: ± 30%
Obsah pevných látek v hmotnosti:	49 - 51 %
Obsah pevných látek v objemu:	40 - 43 %

## DRY TIMES BY 20

Dotykem suché:	1 hour
Suché na manipulaci:	1,5 hours
Suchý nátěr:	4 hours
Plně vytvrzené:	1 day

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

42 µm

## TEORETICKÁ SPOTŘEBA

10 - 15 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

The substrates must be completely dry and clean. On metals, it is necessary to remove old varnish layers (with Rapid Super, for instance) and oxidation traces (with a polish, for instance). Clean afterwards with a cloth soaked in Thinner 22.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Minimum 5°C, maximum temperature 35°C and maximum relative humidity 80 %. No condensation during drying. At low temperature and / or high relative humidity extend these times. The temperature of the substrate must be 3°C above the dew point.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Any type.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Mohair paint roller or short haired roller.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Thinner 22.

## POZNÁMKY

- 2 - 3 coats for outside works.
- 1 - 2 coats for inside works

## DATA SAFETY DATA

Úroveň těkavých organických látek:	499 g/l
VOC readymix:	400 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu