

Quality Paints since 1845
MATHYS[®]



VERNAC SATIN

Acrylic varnish

- Alkaliresistant
- Excellent flexibility
- High weather resistance
- Transparent
- Completely colourless



VERNAC SATIN

POPIS PRODUKTU (DLHÝ)

Solvent based acrylic varnish.

ODPORÚČANÉ POUŽITIE

Protection of non-ferrous metals. Renovation of transparent skylights (except for polycarbonate). Do not apply Vernac Satin as floor varnish or on places that are subject to mechanical pressure.

TECHNICAL DATA

Hustota (g/cm ³):	0,99 - 1,01
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	Satin gloss: ± 30%
Obsah pevných látok v hmotnosti:	49 - 51 %
Obsah pevných látok v objeme:	40 - 43 %

DRY TIMES BY 20

Na dotyk suché:	1 hour
Suché na manipuláciu:	1,5 hours
Suchý na opätovné natieranie:	4 hours
Úplne vytvrdnuté:	1 day

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

42 µm

TEORETICKÁ SPOTREBA

10 - 15 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

The substrates must be completely dry and clean. On metals, it is necessary to remove old varnish layers (with Rapid Super, for instance) and oxidation traces (with a polish, for instance). Clean afterwards with a cloth soaked in Thinner 22.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Minimum 5°C, maximum temperature 35°C and maximum relative humidity 80 %.
No condensation during drying.
At low temperature and / or high relative humidity extend these times. The temperature of the substrate must be 3°C above the dew point.

APLIKÁCIA A RIEDENIE: ŠTETEC

Any type.

APLIKÁCIA A RIEDENIE: VALEC

Mohair paint roller or short haired roller.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Thinner 22.

POZNÁMKY

- 2 - 3 coats for outside works.
- 1 - 2 coats for inside works

DATA SAFETY DATA

Úroveň VOC:	499 g/l
VOC readymix:	400 g/l
Kategória VOC:	A/i
Limit VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu